

# PRODUCT INFORMATION

# ANGLER

ANGLER INDUSTRIES, INC.  
61 Industrial Park Rd • PO Box 217  
Sterling, CT 06377  
860-564-0080 • FAX 860-564-3598  
[www.anglerindustries.com](http://www.anglerindustries.com)



## AccuDraw 900 Emulsifiable, Chlorinated Drawing Oil

### DESCRIPTION

**AccuDraw 900** is a viscous dark brown chlorinated drawing oil which mixes easily into water, forming opaque, off-white emulsions. **AccuDraw 900** begins release of its chlorine to form a pressure resistant barrier as soon as contact is made between work piece and die. This barrier prevents abrasion or rupture of the work piece and preserves the life of the die. The barrier formed by chemically active chlorine is supplemented by a high concentration of emulsifier, which not only imparts extra lubricity, but also provides a desirable metal wetting property for uniformity of oil film coverage. **AccuDraw 900** is inhibited to prevent corrosion.

### APPLICATION

Mix one part of **AccuDraw 900** into 8-10 parts water to form aluminum, brass, cupro-nickel, stainless steel, cold rolled steel and nickel plated cold rolled steel in multi-stage eyelet presses.

For transfer press forming of heavy steel stock, mix one part of **AccuDraw 900** to one part water. Emulsions may be applied to strip or blanks by drip, roller, pad or spray. Parts are best cleaned by an immediate water wash or by an alkaline wash.

### PROPERTIES

VISCOSITY, SSU @100°F	1737
COLOR ASTM	7
FLASH POINT, F	550
POUR POINT, F	15
CHLORINE, %WT.	YES
EMULSION STABILITY (STATIC) 4 HOURS @ 130°F	SLIGHT CUFF

The data in this Product Information sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information set forth herein is furnished free of charge and is based on technical data that **Angler** believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Since conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.